

Catalyst Specification Sheet

Product name: RCAT[®]-9002

Product description: Promoted Sulphur Recovery Catalyst

Appearance: White Sphere

Size: 4-6 mm

Chemical and Physical properties

Property	Min	Max	Typical	Unit
Al ₂ O ₃	88	-	90	%
TiO ₂	4	-	-	%
Bulk density	680	750	700	g/l
BET surface area	200	300	240	m ² /g
Pore volume	0.30	0.45	0.40	ml/g
Crush strength	100	-	120	N

*Values of elemental composition are reported on 900°C calcined basis.

Shipping Information

200 Litre Steel Drum with PE inlay, 140 KG netto per drum, 4 drums on a pallet

Material Classification

Please refer to a valid Material Safety Data Sheet

Ranido Czech Republic

Thákurova 531/4
160 00 Prague 6
Czech Republic
Tel: +420 220 518 805
Email: info@ranido.cz
www.ranido.cz

Ranido R&D Kralupy

Náměstí Georga Karse 7/2
278 01 Kralupy nad Vltavou
Czech Republic
Tel: +420 220 446 106
Email: info@ranido.cz
www.ranido.cz

Ranido Manufacturing Plant

Na Hrázi 124/21
405 02 Děčín VIII - Dolní Oldřichov
Czech Republic
Tel: +420 220 518 805
Email: info@ranido.cz
www.ranido.cz